

## HYGROSMART<sup>®</sup> –ADHESIVE ULTRA-2K

**Two-component, high performance, highly deformable, quick-setting and drying cementitious adhesive with no vertical slip and extended open time for ceramic tiles and stone material**

### DESCRIPTION

**HYGROSMART<sup>®</sup>-ADHESIVE ULTRA-2K** is highly deformable, improved, fast-setting (F) cementitious (C) adhesive, slip resistant (T) and with extended open time (E), complying with the requirements of an adhesive classified as C2FTE.

### RECOMMENDED FOR

Bonding to internal and external walls and floors of all types and sizes of ceramic tiles, natural stones and artificial materials.

### APPLICATIONS

-Laying ceramic and stone floor coverings which are subject to intense traffic.

-Laying tiles on deformable substrates: marine plywood, wooden agglomerates, old wooden floors, etc.

-Quick laying or repair of tiled finishes in places such as swimming pools, refrigeration units, industrial plants.

-Laying even large-sized ceramic and stone tiles on facades, balconies, terraces

-Laying tiles in areas subject to high mechanical stresses and vibration

-Laying tiles on concrete substrates and pre-cast walls.

### APPLICATION PROCEDURE

Substrate Preparation:

Remove oil, grease and wax contaminants, cement laitance, loose particles. Fill surface irregularities with the necessary product.

Mix 25 kg of component A with 6.25 kg of component B. It is best to use a low-speed mechanical mixer to obtain a smooth, homogenous paste.

Apply **HYGROSMART<sup>®</sup>-ADHESIVE ULTRA-2K** on the substrate with a notched trowel. Use a trowel which guarantees that the adhesive is spread well on the back of the tile.

To achieve a good bond, first spread a thin layer of **HYGROSMART<sup>®</sup>-ADHESIVE ULTRA-2K** on the substrate using the smooth side of the trowel, and then immediately apply another layer to the thickness required with a notched trowel according to the type and size of the tile. The tiles must be laid by pressing them down firmly to ensure good contact with the adhesive.

Under normal climatic conditions, the open time of **HYGROSMART<sup>®</sup>-ADHESIVE ULTRA-2K** is approximately 30 minutes. Surfaces tiled with **HYGROSMART<sup>®</sup>-ADHESIVE ULTRA-2K** must not be washed down or exposed to rain for at

## HYGROSMART® –ADHESIVE ULTRA-2K

least 3-4 hours and must be protected from strong, direct sunlight for at least 12 hours.

### CONSUMPTION

Mosaics and small-sized tiles (trowel No.4): 2.5-3 kg/m<sup>2</sup>.

Normal-sized tiles (trowel No. 5): 3.5-4 kg/m<sup>2</sup>

Large tiles and external floors (trowel No. 6): 5-6 kg/m<sup>2</sup>

Uneven back faces and substrates, natural stone (trowel No. 10): 8 kg/m<sup>2</sup> or more.

### CLEANING

Brushes and tools can be cleaned with water. Dried product cannot be cleaned with water and can be removed only by mechanical means.

### PACKAGING

Comp. A: 25kg, Comp. B:6.25kg

**Colour:** grey

### STORAGE

The product can be kept for a minimum of 12 months in the original unopened packaging. Should be stored in dry conditions and at temperatures of 5-25°C. Once opened, use as soon as possible.

### SAFETY

**HYGROSMART®-ADHESIVE ULTRA-2K** contains cement and is therefore irritating. Please use protective equipment and clothing during application.

### TECHNICAL SPECIFICATIONS

| PROPERTY                | UNIT | RESULT    |
|-------------------------|------|-----------|
| Bulk density of Comp. A | Kg/l | 1,50      |
| Density of Comp. B      | Kg/l | 1.00-1,05 |
| pH of Comp. B           | -    | 7-8       |
| Pot life in the pail    | min  | 60-75     |
| Open time               | min  | 30        |

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA S.A. BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. ALCHIMICA S.A. RESERVES THE RIGHT TO CHANGE AT ANY TIME THE PROPERTIES OF ITS PRODUCTS. PLEASE REFER TO THE CURRENT VERSION OF THE TECHNICAL DATA SHEET, AVAILABLE FROM OUR WEB SITE [WWW.ALCHIMICA.COM](http://WWW.ALCHIMICA.COM)

